

### Part 1 - General

#### SUBMITTAL

In accordance with Section 01350 submittal procedures, submit color samples for selection from manufacturer's series. Submit product literature, certifications, test reports and full size sample(s) of each color specified. Provide current integral water repellent CMU producer qualification.

#### QUALITY ASSURANCE

**Certifications (Smooth, Split-Face, Tumbleridge Finishes):** Nettbrick units are hollow and solid non-load bearing concrete masonry units with faces that are either smooth, split utilizing blades exerting pressure from all four sides of product, or Tumbleridge utilizing a drum roller after product has been split. Units are manufactured by means of moisture controlled curing for 24 hours minimum. Concrete blocks for finishing shall conform to ASTM C90 for Normal Weight. All units contain an integral water repellent CMU admixture at the time of manufacture. Units shall conform to ASTM C744 with respect to abrasion, crazing resistance, and color change.

**Fire Resistance:** Define hourly ratings required as 1, 2, 3, or 4 hours.

**Field Constructed Mock-Ups:** Construct a sample panel no less than 4' x 6' containing each color and size units to be used in the project illustrating color, clear sealer finish, texture, and mortar joints to establish a standard of quality for completed work. Mock-Up shall also illustrate Nettbrick and mortar combination, coursing, bond, and pattern. Retain mock-up during construction as a quality standard. Completely remove when work is accepted.

#### DELIVERY, STORAGE AND HANDLING

Nettbrick units shall be delivered on covered wood pallets in such a way as to protect faces. Store in protected area and covered to ensure units remain dry and clean. Do not allow units to sit in standing water. Handle masonry units in manner to avoid chipping, breaking, contact with contaminating materials, and marring of faces.

### Part 2 – Products

#### PRODUCT NAME

Nettbrick Custom 4" Concrete Masonry Veneer

#### MANUFACTURER

Nettleton Concrete, Inc. (800) 382-2462  
P.O. Box 2157 · Jonesboro, Arkansas 72402

#### RELATED MATERIALS

Colored matching or contrasting mortar is available from the manufacturer. For all exterior mortar, use matching manufacturer approved water-repellent mortar additive, following manufacturer's instructions.

#### FINISHES

Smooth Face, Split Face, and Tumbleridge Nettbrick are available.

#### SIZES AND SHAPES

Nominal 4", 8", 12" standard block thicknesses are available.

#### WATER REPELLENCY

Nettbrick Units are manufactured with RainBloc® integral water repellent, or approved equal, to assist in controlling efflorescence. Use of RainBloc® mortar admixture, or approved equal, is required for a water repellent wall.

#### MASONRY CLEANER

Use masonry cleaners such as Specialty Masonry Cleaner, manufactured by Diedrich Technologies, Inc., or approved equal for all finishes. Do not apply cleaner with a pressure sprayer above 50psi.

### Part 3 – Execution

#### INSTALLATION

Install Nettbrick as part of unit masonry work specified in Section 04850 - Unit Masonry Assemblies. Always lay blocks from more than one pallet at a time during installation. Complete masonry construction using procedures and workmanship consistent with quality masonry practices.

**Cutting:** Field cut Nettbrick with motor-driven masonry saws using an abrasive or diamond blade to provide straight true edges and avoid damage to face. Field split Nettbrick corners with suitable tools to insure uniform texture and consistency of face. Do not install chipped or broken units.

**Mortar Bedding and Jointing:** All mortar joints should be tuckpointed for the appropriate appearance. For external applications, tuckpoint joints to control water penetration. Raked joints are not recommended for any application.

**Protection:** During erection, cover top of walls with waterproof sheeting at end of each day. Cover partially completed walls when work is not in progress. Extend cover 24 inches minimum down both sides and hold securely in place. Protect face of walls, sills, and other projections from roof run-off, splashed water, mud, grout, and mortar. Spread sand or straw at base of walls to minimize dirt and clay splashing onto Nettbrick faces. Without damaging completed work, it is recommended to provide protective boards at exposed external corners which may be damaged by construction activities.

#### INSPECTION

Faces of units exposed in finished work shall be of uniform color and texture and free of chips, cracks, or other imperfections detracting from appearance of the finished wall when viewed from a distance of fifteen (15) feet at right angles to the wall under normal lighting conditions.

#### FLASHING OF MASONRY WORK

Install flashing at locations shown in the plans and in strict accordance with the details and quality masonry flashing practices.

#### WEEP HOLES AND VENTS

Install weep holes and vents at proper intervals at courses above grade, above flashing, and at any water stops over windows, doors and beams.

#### CLEANING

Exercise care that wet mortar is not splashed onto Nettbrick during installation. Excess or splashed mortar shall be cleaned from face with dry burlap wipe or masonry brush. Remove after mortar becomes hard enough not to smear but prior to mortar setting.

#### FINAL CLEANDOWN

Clean completed wall surfaces using masonry cleaners such as Specialty Masonry Cleaner, manufactured by Diedrich Technologies, Inc. Dilute cleaning solution as recommended by manufacturer. Strictly follow manufacturers cleaning instructions. Do not use acid or abrasives on finished surfaces. Do not powerwash. High pressure powerwashing may interfere with performance of the integral water repellent causing efflorescence.

#### MAINTENANCE

Nettbrick, properly installed, cleaned, and sealed, need virtually no maintenance other than routine cleaning with standard commercial grade cleaning agents. Contact manufacturer for specific cleaning recommendations.